



Field 2


kvadrat




463




663




443




623



643



843




343



673




662




242




132



373



182




173



693


Field 2



733




222




233




123



763




723



142



782




793



192



943




963



773



983



933



Field 2

Abrasion

Approx. 80.000 Martindale rubs, EN ISO 12947

Abrasion test results exceeding ACT performance guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention

Pilling

Note 4-5, EN ISO 12945

Seam slippage

Seam parallel to warp: 4.0 mm parallel to weft: 3.5 mm
EN ISO 13 936-2 180 Newton

Lightfastness

Note 6-7 ISO 105-B02

Fastness to rubbing

Dry note 4-5 ISO 105-X12

Wet note 4-5 ISO 105-X12

Absorption

0.55/Class D (flat), 0.85/Class B (waved) EN ISO 354

Airflow

431 Pa s/m EN 29053

Flame resistance

AS/NZS 3837 class 1

ASTM E84 Class A Unadhered

BS 5852 Crib 5

BS 5867 Part 2 type B

CAN ULC S102

CAN ULC S109

DIN 4102 B1

EN 1021-1/2

EN 13501-1 B-s1, d0

FAR 25.853

GB 8624 B1

IMO FTP Code 2010 Part 5

IMO FTP Code 2010 Part 8

NF D 60 013

NF P 92 507 M1

NFPA 701

ÖNORM B1/Q1

SN 198 898 5.2

UNI 9175 1IM

UNI 9177 Classe 1

US Cal. Bull. 117-2013

Field 2

Design: Alfredo Häberli

Type: Upholstery, panel fabric

In accordance with California Bill AB 2998 and similar legislation within the United States, this product may not be used as upholstery. It can be used for vertical applications.

Composition: 100% Trevira CS

Yarn type: Filament

Binding: Panama

Width: Approx. 140 cm, 55 inches

Weight: Approx. 450 g/lin.m, 14.5 oz/ly

Repeat: None

Colour difference may occur

Cleaning: Vacuum clean frequently, ideally every week if fixed covers. Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary. Extraction cleaning might dissolve water-based glue. Pay attention to temperature and amount of cleaning fluid.

Also washable at 60-80°C, half wash load. Drip drying.

Mount in moist condition. Shrinkage app. 2% at 60°C.

Be aware of increased shrinking and creasing the higher the temperature.

Disinfection, see kvadrat.dk

More info: Care and maintenance kvadrat.dk



10 year
warranty



0575/22

Acoustic



kvadrat

ACT Guidelines Woven fabrics

Flammability

US Cal. Bull. 117-2013

Dry & Wet Crocking

Dry Crocking: Grade 5.0

Wet Crocking: Grade 5.0

Colour Fastness to Light

Grade 4.5 minimum 40 hours

Physical properties

Pilling Class 4-5

Breaking Strength warp 274 / weft 282 lbs.

Seam Slippage warp 98.5 / weft 93.5 lbs.

Abrasion

80.000 cycles Martindale – High Traffic / Public Spaces

Quality benefits

Complies with Möbelfakta

Very good abrasion

Very good lightfastness

Permanent flame retardant

Washable

Environmental benefits

EU Ecolabel compliant

Free of intentionally added PFAS

No use of halogen-based flame retardants (incl. brominated and chlorinated)

REACH compliant

Californian Proposition 65 list compliant

LBC Red list compliant

Mono material designed for circularity

Green building certificates

Greenguard Gold: Low chemical emission

Environmental Product Declaration (EPD): 3rd Party Verified.

ISO 14025 & EN 15804. Developed in accordance with the European standard EN 15804+A2.

Health Product Declaration (HPD): Declaring textile content and substance

Country of origin

Holland

Launch

2008

Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard material is FSC certified and / or contains recycled content.

For further information

kvadrat.dk