



Floyd

kvadrat

Floyd



983




623




663




643




693



943




923




263




963



213




243




413




103




123




223




763




723




143




363




783



793



193



163



Floyd

Abrasion

Approx. 50.000 Martindale rubs, EN ISO 12947

Abrasion test results exceeding ACT performance guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention

Pilling

Note 3-4, EN ISO 12945

Seam slippage

Seam parallel to warp: 5.0 mm parallel to weft: 2.5 mm
EN ISO 13 936-2 180 Newton

Lightfastness

Note 6-7 ISO 105-B02

Fastness to rubbing

Dry note 4-5 ISO 105-X12

Wet note 4-5 ISO 105-X12

Absorption

0.50/Class D (flat), 0.80/Class B (waved) EN ISO 354

Airflow

689 Pa s/m EN 29053

Flame resistance

AS/NZS 3837 class 2

ASTM E84 Class A Adhered

ASTM E84 Class A Unadhered

BS 5852 crib 5 with treatment *

BS 5852 part 1 with treatment *

EN 1021-1/2

IMO FTP Code 2010 Part 8

NPFA 701 with treatment

US Cal. Bull. 117-2013

Free from added flame retardant chemicals as standard

** To pass this test flame retardant treatment is necessary. We are looking into more environmentally friendly alternatives but for now, the external finisher may use a treatment containing halogen-based flame retardants*

Floyd

Design: Åsa Pärson

Type: Upholstery, panel fabric

Composition: 50% polyester, 45% new wool, 5% nylon

Yarn type: Worsted

Binding: Plain weave

Width: Approx. 140 cm, 55 inches

Weight: Approx. 370 g/lin.m, 11.9 oz/ly

Repeat: None

Colour difference may occur

Foreign fibres may occur in light colours

Cleaning: Vacuum clean frequently, ideally every week.

Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary.

Extraction cleaning might dissolve water-based glue. Pay attention to temperature and amount of cleaning fluid.

Disinfection, see kvadrat.dk

More info: Care and maintenance kvadrat.dk



10 year warranty



kvadrat

ACT Guidelines Woven fabrics

Flammability

US Cal. Bull. 117-2013

Dry & Wet Crocking

Dry Crocking: Grade 4.5

Wet Crocking: Grade 4.5

Colour Fastness to Light

Grade 4.5 minimum 40 hours

Physical properties

Pilling Class 3-4

Breaking Strength warp 198 / weft 160 lbs.

Seam Slippage warp 123.5 / weft 34.5 lbs.

Abrasion

50.000 cycles Martindale – High Traffic / Public Spaces

Benefits of wool

Wool is a renewable resource

Wool is very comfortable because of its ability to absorb/
give off humidity

Wool is flame retardant

Wool is biodegradable

Wool is naturally soil resistant

Wool ages with grace

Quality benefits

Complies with Möbelfakta

Good abrasion

Very good lightfastness

Flame retardant

Environmental benefits

Follow the EU Ecolabel dye restrictions incl. AZO dye
and heavy metal restrictions

Free of intentionally added PFAS

REACH compliant

Californian Proposition 65 list compliant

LBC Red list compliant

Healthier Hospitals compliant

Green building certificates

Greenguard Gold: Low chemical emission

Environmental Product Declaration (EPD): 3rd Party Verified.

ISO 14025 & EN 15804. Developed in accordance with the
European standard EN 15804+A2.

Health Product Declaration (HPD): Declaring textile content
and substance

Country of origin

United Kingdom

Launch

2016

Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard
material is FSC certified and / or contains recycled content.

For further information

kvadrat.dk