

Maple

**kvadrat**

Maple




732



832



542




162




742



722



132



762




792



112



102



192

# Maple




342



332



212



662




222



202




362



562



232




862




352



392



172



142



## Maple

Design: Åsa Pårsom

Type: Upholstery, low traffic contract and soft seating.  
*Due to the irregular nature of the chenille yarn, the colour and look will vary, contributing to the natural characteristics of the textile. The pile of the chenille yarn is multi directional giving a varying light reflection over the surface. Colours will appear within a range of tones according to the varying light reflection. The different directions of the pile appear randomly, giving each piece its own characteristics.*

Composition: 81% viscose, 15% linen, 4% polyester, non-woven polyester backing

Yarn type: Chenille

Binding: Plain

Width: Approx. 140 cm, 55 inches

Weight: Approx. 910 g/lin.m, 29.2 oz/ly

Repeat: None

Colour difference may occur



10 year warranty



# Maple

## Abrasion

Approx. 30.000 Martindale rubs, EN ISO 12947

## Pilling

Note 4-5, EN ISO 12945

## Seam slippage

Seam parallel to warp: 2.0 mm parallel to weft: 2.0 mm  
EN ISO 13 936-2 180 Newton

## Lightfastness

Note 5-7 ISO 105-B02

## Fastness to rubbing

Dry note 4-5 ISO 105-X12

Wet note 4-5 ISO 105-X12

## Absorption

0.45/Class D (flat), 0.70/Class C (waved) EN ISO 354

## Airflow

7455 Pa s/m EN 29053

## Flame resistance

AS/NZS 1530.3

AS/NZS 3837 class 2

BS 5852 crib 5 with treatment \*

BS 5852 part 1

EN 1021-1/2

IMO FTP Code 2010 Part 8

NFPA 260

US Cal. Bull. 117-2013 with treatment (AB 2998 compliant)

Free from added flame retardant chemicals as standard

*\* To pass this test flame retardant treatment is necessary. We are looking into more environmentally friendly alternatives but for now, the external finisher may use a treatment containing halogen-based flame retardants*

## ACT Guidelines Woven fabrics

### Flammability

US Cal. Bull. 117-2013

### Dry & Wet Crocking

Dry Crocking: Grade 4.5

Wet Crocking: Grade 4.0

### Colour Fastness to Light

Grade 4.0 minimum 40 hours

### Physical properties

Pilling Class 4-5

Breaking Strength warp 237 / weft 142 lbs.

Seam Slippage warp 105.5 / weft 88 lbs.

### Abrasion

30.000 cycles Martindale – Low Traffic / Private Spaces

### Quality benefits

Good abrasion

Good lightfastness

Flame retardant

### Environmental benefits

Renewable resources

No content of PFCs or 'PFAS'

REACH compliant

Californian Proposition 65 list compliant

LBC Red list compliant

Healthier Hospitals compliant

### Green building certificates

Greenguard Gold: Low chemical emission

Health Product Declaration (HPD): Declaring textile content and substance

### Country of origin

Turkey

### Launch

2017

### Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard material is FSC certified and / or contains recycled content.

For further information

kvadrat.dk

## Cleaning and Maintenance

Maple is constructed from chenille yarns which create a subtle three-dimensional expression on the textile's surface. As a result, shading and pressure marks will occur during usage and cleaning. These are typically properties of chenille textiles.

We recommend vacuuming the textile in the pile direction frequently, ideally every week. Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary.

Extraction cleaning might dissolve water-based glue. Pay attention to temperature and amount of cleaning fluid.

Darker spots from water spills or because of stain removal can occur. In addition, pressure marks can occur during usage.

Spots and pressure marks can be removed by brushing the textiles with a soft brush in moist condition and in direction of the pile. Moisten the textile by placing a damp cloth on the whole surface or spraying it with distilled water. Let the textile dry completely before usage.

Disinfection, see kvadrat.dk

More info: Care and maintenance kvadrat.dk

