


Memory 2

kvadrat


Memory 2



143



116



193




176




793




123



453



156



236




223



213



713



473



256



613



976



673



653



936



953



Memory 2

Abrasion

Approx. 35.000 Martindale rubs, EN ISO 12947

Pilling

Note 4, EN ISO 12945

Seam slippage

Seam parallel to warp: 2.0 mm parallel to weft: 2.0 m
EN ISO 13 936-2 180 Newton

Lightfastness

Note 5-8 ISO 105-B02

Fastness to rubbing

Dry note 4-5 ISO 105-X12
Wet note 4-5 ISO 105-X12

Absorption

0.65/Class C (flat), 0.85/Class B (waved) EN ISO 354

Airflow

2075 Pa s/m EN 29053

Flame resistance

AS/NZS 3837 class 1
ASTM E84 Class A Unadhered
BS 5852 crib 5 with treatment *
BS 7176 Low Hazard
DIN 4102 B1
EN 1021-1/2
EN 13501-1, B-s1, d0
GB 8624 B1
IMO FTP Code 2010 Part 5
IMO FTP Code 2010 Part 8
JIS L 1091 A-1 D
NF D 60 013
NF P 92 507 M1
NFPA 260
NFPA 701
ÖNORM B1/Q1
SN 198 898 5.2
UNI 9175 1IM
UNI 9177 Classe 1
US Cal. Bull. 117-2013

* To pass this test flame retardant treatment is necessary.
We are looking into more environmentally friendly alternatives but for now, the external finisher may use a treatment containing halogen-based flame retardants

Memory 2

Design: Patricia Urquiola

Type: Upholstery, panel fabric

In accordance with California Bill AB 2998 and similar legislation within the United States, this product may not be used as upholstery. It can be used for vertical applications.

Composition: 100% Trevira CS

Yarn type: Filament

Binding: Jacquard

Width: Approx. 140 cm, 55 inches

Weight: Approx. 650 g/lin.m, 21 oz/ly

Repeat: Approx. 144 cm, 56.5 inches V / 140 cm, 55 inches H

Colour difference may occur

Cleaning: Vacuum clean frequently, ideally every week if fixed covers. Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary. Extraction cleaning might dissolve water-based glue. Pay attention to temperature and amount of cleaning fluid.

Also washable at 60-80°C, half wash load. Drip drying.

Mount in moist condition. Shrinkage app. 2% at 60°C.

Be aware of increased shrinking and creasing the higher the temperature.

Disinfection, see kvadrat.dk

More info: Care and maintenance - kvadrat.dk



10 year warranty



kvadrat

ACT Guidelines Woven fabrics

Flammability

US Cal. Bull. 117-2013

Dry & Wet Crocking

Dry Crocking: Grade 5.0

Wet Crocking: Grade 5.0

Colour Fastness to Light

Grade 4.0 minimum 40 hours

Physical properties

Pilling Class 4

Breaking Strength warp 319 / weft 191 lbs.

Seam Slippage warp 133 / weft 150 lbs.

Abrasion

35.000 cycles Martindale – Low Traffic / Private Spaces

Quality benefits

Good abrasion

Very good lightfastness

Permanent flame retardant

Washable

Environmental benefits

Follow the EU Ecolabel dye restrictions incl. AZO dye and heavy metal restrictions

No use of halogen-based flame retardants (incl. brominated and chlorinated)

Free of intentionally added PFAS

Mono-material designed for circularity

REACH compliant

Californian Proposition 65 list compliant

LBC Red list compliant

Green building certificates

Greenguard Gold: Low chemical emission

Environmental Product Declaration (EPD): 3rd Party Verified.

ISO 14025 & EN 15804. Developed in accordance with the

European standard EN 15804+A2.

Health Product Declaration (HPD): Declaring textile content and substance

Country of origin

Holland

Launch

2013

Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard material is FSC certified and / or contains recycled content.

For further information

kvadrat.dk